



Glass Thickness	Spacer	OD	U-Value Btu/h-ft <sup>2</sup> -F <sup>2</sup>	U-Value W/m <sup>2</sup> -K <sup>2</sup>	SHGC	CR	ER	CND Energy Star Zone	USA Energy Star Zone
-----------------	--------	----	--	---	------	----	----	-------------------------	-------------------------

### 260 Awning

#### SOL-R®-I 178 / Clear

3/3mm	XL Edge SS	0.75	0.27	1.51	0.58	59	41	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.57	59	40	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	1	0.28	1.57	0.57	57	39	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.56	56	39	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	1	0.27	1.55	0.56	56	39	A, B, C	N, NC, SC, S
6/5mm	XL Edge SS	1	0.27	1.53	0.55	56	38	A, B, C	N, NC, SC, S
3/3mm	XL Edge SS	1	0.28	1.60	0.58	57	39	A	N, NC, SC, S

#### SOL-R®-I 270 / Clear

3/3mm	XL Edge SS	0.75	0.25	1.41	0.37	60	30	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.36	60	30	A, B, C, D	N, NC, SC, S
3/3mm	XL Edge SS	1	0.26	1.50	0.37	58	28	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	1	0.26	1.48	0.36	58	28	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.36	57	29	A	N, NC, SC, S
5/5mm	XL Edge SS	1	0.25	1.45	0.36	57	29	A	N, NC, SC, S
6/5mm	XL Edge SS	1	0.25	1.43	0.35	57	29	A	N, NC, SC, S

#### SOL-R®-I 366 / Clear

3/3mm	XL Edge SS	0.75	0.24	1.36	0.27	61	26	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.27	61	26	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	1	0.25	1.42	0.27	58	25	A, B, C, D	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.25	1.42	0.28	58	25	A, B, C, D	N, NC, SC, S
5/5mm	XL Edge SS	1	0.25	1.42	0.27	57	25	A, B, C, D	N, NC, SC, S
6/5mm	XL Edge SS	1	0.25	1.42	0.27	57	25	A, B, C, D	N, NC, SC, S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
 + Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
 + SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup>-F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup>-K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
3/3mm	XL Edge SS	1	0.26	1.48	0.27	58	23	A, B, C	N, NC,SC,S
<b>Bronze / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.49	60	35	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.47	60	34	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.46	57	32	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.43	57	31	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	1	0.27	1.55	0.43	56	31	A, B, C	N, NC,SC,S
6/5mm	XL Edge SS	1	0.27	1.53	0.39	56	29	A, B, C	N, NC,SC,S
3/3mm	XL Edge SS	1	0.28	1.60	0.49	57	33	A	N, NC,SC,S
<b>Bronze / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.36	61	30	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.34	61	29	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.50	0.36	58	28	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.26	1.48	0.34	58	27	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.32	58	27	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.32	57	27	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.29	57	26	A	N, NC,SC,S
<b>Bronze / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.31	61	28	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.29	61	27	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.28	58	25	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.27	57	25	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.25	57	24	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.47	0.31	59	25	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.29	59	25	A	N, NC,SC,S
<b>Green / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.50	60	36	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.47	60	34	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.47	57	33	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.44	57	32	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	1	0.27	1.55	0.44	56	31	A, B, C	N, NC,SC,S
3/3mm	XL Edge SS	1	0.28	1.60	0.49	57	33	A	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft -F<sup>2</sup></b>	<b>U-Value W/m -K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
<b>Green / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.39	61	32	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.38	61	31	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.50	0.39	58	30	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.26	1.48	0.38	58	29	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.37	58	30	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.36	57	29	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.34	57	29	A	N, NC,SC,S
<b>Green / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.35	61	30	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.34	61	30	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.33	58	28	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.33	57	28	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.31	57	28	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.47	0.35	59	28	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.34	59	28	A	N, NC,SC,S
<b>Grey / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.47	60	34	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.45	60	33	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.44	57	31	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.41	57	30	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	1	0.27	1.55	0.41	56	30	A, B, C	N, NC,SC,S
6/5mm	XL Edge SS	1	0.27	1.53	0.37	56	28	A, B, C	N, NC,SC,S
3/3mm	XL Edge SS	1	0.28	1.60	0.47	57	32	A	N, NC,SC,S
<b>Grey / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.35	61	29	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.33	61	28	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.50	0.34	58	27	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.26	1.48	0.32	58	26	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.31	58	26	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.30	57	26	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.28	57	25	A	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup>-F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup>-K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
<b>Grey / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.29	61	27	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.28	61	26	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.26	58	24	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.26	57	24	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.24	57	23	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.47	0.29	59	25	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.28	59	24	A	N, NC,SC,S
<b>Lam / 178</b>									
5/3mm	XL Edge SS	0.75	0.27	1.54	0.58	57	40	A, B, C	N, NC,SC,S
6/4mm	XL Edge SS	1	0.27	1.52	0.57	56	40	A, B, C	N, NC,SC,S
6/6mm	XL Edge SS	1	0.26	1.48	0.57	56	40	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.30	1.68	0.58	57	37	A, B	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.30	1.68	0.57	57	36	A, B	N, NC,SC,S
<b>Lam / 270</b>									
6/4mm	XL Edge SS	1	0.25	1.42	0.43	57	34	A, B, C, D	N, NC,SC,S
6/6mm	XL Edge SS	1	0.24	1.38	0.43	57	34	A, B, C, D	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.28	1.58	0.43	58	30	A, B, C	N, NC,SC,S
5/3mm	XL Edge SS	0.75	0.25	1.44	0.43	58	33	A	N, NC,SC,S
<b>Lam / 366</b>									
5/3mm	XL Edge SS	0.75	0.25	1.40	0.37	58	31	A, B, C, D	N, NC,SC,S
6/4mm	XL Edge SS	1	0.24	1.39	0.37	57	31	A, B, C, D	N, NC,SC,S
6/6mm	XL Edge SS	1	0.24	1.35	0.37	57	32	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.55	0.37	58	27	A, B, C	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.27	1.55	0.37	58	27	A, B, C	N, NC,SC,S

### 260 Casement

#### SOL-R®-I 178 / Clear

3/3mm	XL Edge SS	0.75	0.27	1.51	0.58	60	41	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.57	60	40	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.57	59	39	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.56	58	39	A, B, C	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup> -F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup> -K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
5/5mm	XL Edge SS	1	0.27	1.55	0.56	59	39	A, B, C	N, NC, SC, S
6/5mm	XL Edge SS	1	0.27	1.53	0.55	59	38	A, B, C	N, NC, SC, S
3/3mm	XL Edge SS	1	0.28	1.60	0.58	59	39	A	N, NC, SC, S
<b>SOL-R®-I 270 / Clear</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.37	62	30	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.36	62	30	A, B, C, D	N, NC, SC, S
3/3mm	XL Edge SS	1	0.26	1.50	0.37	60	28	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	1	0.26	1.48	0.36	60	28	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.36	59	29	A	N, NC, SC, S
5/5mm	XL Edge SS	1	0.25	1.45	0.36	60	29	A	N, NC, SC, S
6/5mm	XL Edge SS	1	0.25	1.43	0.35	60	29	A	N, NC, SC, S
<b>SOL-R®-I 366 / Clear</b>									
3/3mm	XL Edge SS	0.75	0.24	1.36	0.27	62	26	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.27	62	26	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	1	0.25	1.42	0.27	61	25	A, B, C, D	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.25	1.42	0.28	59	25	A, B, C, D	N, NC, SC, S
5/5mm	XL Edge SS	1	0.25	1.42	0.27	61	25	A, B, C, D	N, NC, SC, S
6/5mm	XL Edge SS	1	0.25	1.42	0.27	61	25	A, B, C, D	N, NC, SC, S
3/3mm	XL Edge SS	1	0.26	1.48	0.27	61	23	A, B, C	N, NC, SC, S
<b>Bronze / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.49	61	35	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.47	61	34	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	1	0.28	1.57	0.46	59	32	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.43	58	31	A, B, C	N, NC, SC, S
5/5mm	XL Edge SS	1	0.27	1.55	0.43	59	31	A, B, C	N, NC, SC, S
6/5mm	XL Edge SS	1	0.27	1.53	0.39	59	29	A, B, C	N, NC, SC, S
3/3mm	XL Edge SS	1	0.28	1.60	0.49	59	33	A	N, NC, SC, S
<b>Bronze / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.36	62	30	A, B, C, D	N, NC, SC, S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.34	62	29	A, B, C, D	N, NC, SC, S
3/3mm	XL Edge SS	1	0.26	1.50	0.36	60	28	A, B, C	N, NC, SC, S
4/4mm	XL Edge SS	1	0.26	1.48	0.34	60	27	A, B, C	N, NC, SC, S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup>-F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup>-K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
5/5mm	XL Edge SS	0.75	0.25	1.44	0.32	59	27	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.32	60	27	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.29	60	26	A	N, NC,SC,S
<b>Bronze / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.31	62	28	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.29	62	27	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.28	59	25	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.27	61	25	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.25	61	24	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.47	0.31	61	25	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.29	61	25	A	N, NC,SC,S
<b>Green / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.50	61	36	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.47	61	34	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.47	59	33	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.44	58	32	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	1	0.27	1.55	0.44	59	31	A, B, C	N, NC,SC,S
3/3mm	XL Edge SS	1	0.28	1.60	0.49	59	33	A	N, NC,SC,S
<b>Green / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.39	62	32	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.38	62	31	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.50	0.39	60	30	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.26	1.48	0.38	60	29	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.37	59	30	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.36	60	29	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.34	60	29	A	N, NC,SC,S
<b>Green / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.35	62	30	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.34	62	30	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.33	59	28	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.33	61	28	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.31	61	28	A, B, C, D	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup>-F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup>-K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
3/3mm	XL Edge SS	1	0.26	1.47	0.35	61	28	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.34	61	28	A	N, NC,SC,S
<b>Grey / 178</b>									
3/3mm	XL Edge SS	0.75	0.27	1.51	0.47	61	34	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.26	1.50	0.45	61	33	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.28	1.57	0.44	59	31	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.54	0.41	58	30	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	1	0.27	1.55	0.41	59	30	A, B, C	N, NC,SC,S
6/5mm	XL Edge SS	1	0.27	1.53	0.37	59	28	A, B, C	N, NC,SC,S
3/3mm	XL Edge SS	1	0.28	1.60	0.47	59	32	A	N, NC,SC,S
<b>Grey / 270</b>									
3/3mm	XL Edge SS	0.75	0.25	1.41	0.35	62	29	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.25	1.39	0.33	62	28	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.50	0.34	60	27	A, B, C	N, NC,SC,S
4/4mm	XL Edge SS	1	0.26	1.48	0.32	60	26	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.44	0.31	59	26	A	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.45	0.30	60	26	A	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.43	0.28	60	25	A	N, NC,SC,S
<b>Grey / 366</b>									
3/3mm	XL Edge SS	0.75	0.24	1.37	0.29	62	27	A, B, C, D	N, NC,SC,S
4/4mm	XL Edge SS	0.75	0.24	1.36	0.28	62	26	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.25	1.40	0.26	59	24	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	1	0.25	1.41	0.26	61	24	A, B, C, D	N, NC,SC,S
6/5mm	XL Edge SS	1	0.25	1.40	0.24	61	23	A, B, C, D	N, NC,SC,S
3/3mm	XL Edge SS	1	0.26	1.47	0.29	61	25	A	N, NC,SC,S
4/4mm	XL Edge SS	1	0.25	1.44	0.28	61	24	A	N, NC,SC,S
<b>Lam / 178</b>									
5/3mm	XL Edge SS	0.75	0.27	1.54	0.58	58	40	A, B, C	N, NC,SC,S
6/4mm	XL Edge SS	1	0.27	1.52	0.57	59	40	A, B, C	N, NC,SC,S
6/6mm	XL Edge SS	1	0.26	1.48	0.57	59	40	A, B, C	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.30	1.68	0.58	58	37	A, B	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.30	1.68	0.57	58	36	A, B	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient

<b>Glass Thickness</b>	<b>Spacer</b>	<b>OD</b>	<b>U-Value Btu/h-ft<sup>2</sup>-F<sup>2</sup></b>	<b>U-Value W/m<sup>2</sup>-K<sup>2</sup></b>	<b>SHGC</b>	<b>CR</b>	<b>ER</b>	<b>CND Energy Star Zone</b>	<b>USA Energy Star Zone</b>
<b>Lam / 270</b>									
6/4mm	XL Edge SS	1	0.25	1.42	0.43	60	34	A, B, C, D	N, NC,SC,S
6/6mm	XL Edge SS	1	0.24	1.38	0.43	60	34	A, B, C, D	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.28	1.58	0.43	59	30	A, B, C	N, NC,SC,S
5/3mm	XL Edge SS	0.75	0.25	1.44	0.43	59	33	A	N, NC,SC,S
<b>Lam / 366</b>									
5/3mm	XL Edge SS	0.75	0.25	1.40	0.37	59	31	A, B, C, D	N, NC,SC,S
6/4mm	XL Edge SS	1	0.24	1.39	0.37	61	31	A, B, C, D	N, NC,SC,S
6/6mm	XL Edge SS	1	0.24	1.35	0.37	61	32	A, B, C, D	N, NC,SC,S
5/5mm	XL Edge SS	0.75	0.27	1.55	0.37	59	27	A, B, C	N, NC,SC,S
6/4mm	XL Edge SS	0.75	0.27	1.55	0.37	59	27	A, B, C	N, NC,SC,S

**Legend:** + USA Energy Star Designations: "N" = Northern, "NC" = North/Central, "SC" South/Central, "S" = Southern  
+ Standards: U-values = NFRC100-01; SHGC/VT = NFRC 200-01; CR = NFRC 500-01; ER = CAN/CSA A440.02-04  
+ SHGC = Solar Heat Gain Coefficient